




Novec™ Fluorosurfactant FC-4430

Product Information



Introduction

3M™ Novec™ Fluorosurfactant FC-4430 is a non-ionic polymeric fluorochemical surfactant belonging to a class of coating additives which provide low surface tensions in organic coating systems that are best obtainable with fluorochemicals. Novec FC-4430 fluorosurfactant is an excellent wetting, leveling and flow control agent for a variety of waterborne, solvent-borne, high-solids and radiation curable organic polymer coating systems. Novec FC-4430 fluorosurfactant is soluble and compatible with most polymers and continues to be active throughout the drying or curing process. When used in waterborne polymer systems, Novec FC-4430 fluorosurfactant tends to reduce the aqueous/organic interfacial tension and remain surface active in the organic portion of the polymer system.

Novec FC-4430 fluorosurfactant is the first in a new line of fluorochemical surfactants from 3M based on perfluorobutane sulfonate (PFBS). PFBS refers collectively to perfluorobutane sulfonyl compounds including perfluorobutane sulfonates. 3M believes PFBS-based surfactants, with only four perfluorinated carbon atoms, offer improved environmental properties.

PFBS EHS Summary

- Low toxicity
 - Low mammalian toxicity
 - Low ecotoxicity
- Bioconcentration factor <1

Typical Physical Properties

Not for specification purposes

All values determined at 77°F (25°C) unless otherwise specified

Properties	FC-4430
Appearance	Slightly hazy/clear, yellow viscous liquid
Specific gravity	1.14 g/cc
Flash point (Setaflash closed cup)	180 °F (82 °C)
pH (of 1% aqueous solution)	4.5
Boiling point	392 °F (200 °C)
Vapor pressure	0.0014 psi (0.07mm Hg)
Viscosity (Brookfield, #3, 6 rpm)	4000-6000 cps
Solubility in water	Dispersible in all proportions
Tg	< 0°C
Type	Non-ionic
Composition	90% polymeric fluorochemical actives 8% non-fluorochemical actives 2% co-solvent (NMP, toluene)
Freeze/thaw stability	Protect from freezing*

*If material freezes, warm it to >30°C until fluid. Freezing will not change physical properties or adversely affect performance.

3M™ Novec™ Fluorosurfactant FC-4430 Use Recommendations

Recommended use level is between 0.05% and 0.3% active surfactant; however, use level can vary depending on the use and concentration of other additives and solvents in the formulation. Novec FC-4430 fluorosurfactant is effective in water-borne systems. It is suggested, however, that a 10-25% active surfactant solution be prepared with water-miscible solvent prior to addition. Recommended solvents include dipropylene glycol mono methyl ether (DPM), isopropyl alcohol, butyl cellusolve or other water-miscible solvents common to coating systems.

FC-4430 Static Surface Tension

All values determined at 77°F (25°C) unless otherwise specified

Surface Tension (dynes/cm) @ % FC-4430 in solvent/resin

Solvent / Resin	0.0	0.1	0.2	0.5%
Distilled Water	73	21	21	20
ARCOL LG-56	33	30	28	23
Dibutyl Phthalate	34	33	32	31
Cycloaliphatic epoxy resin (UVR-6110, UC)	46	38	36	23
Diglycidylether bisphenol A epoxy resin (828-RS)	45	33	29	17


Interfacial Surface Tensions

Surfactant	Interfacial Tension (dynes/cm) Light Phase: Heptane			Interfacial Tension (dynes/cm) Light Phase: Cyclohexane		
	200ppm	0.5%	1.0%	200ppm	0.5%	1.0%
Control		43.7			51.2	
FC-4430	3.5	2.2		2.5	1.5	
FC-430	3.5	2.4		4.0	2.1	
SDS ¹	15.4	6.1	5.8	12.9	5.0	4.9
SDS-10 ²	15.9	4.1	3.7	13.5	2.9	2.6
Silicone Dispersant	14.4	10.9	10.5	11.7	8.8	8.8

¹Sodium dodecyl sulfate

²Sodium dodecyl benzene sulfonate

Surface Tension vs Bubble Frequency in Water




3M™ Novec™ Fluorosurfactant FC-4430 Solubility

All values determined at 77°F (25°C) unless otherwise specified

Solvent	Grams of FC-4430 / 100 ml of solvent
Methyl Alcohol	>25
Butyl Cellosolve	>25
Cellosolve Acetate	>35
Cellosolve	>25
Methyl Ethyl Ketone	>25
Toluene	>35
Dimethylformamide	>25
ARCOL LG-56	>40
Phenyl Glycidyl Ether	>30
Dibutyl Phthalate	>25
Heptane	<1
Mineral Spirits	<1

Surface Tension/CMC (in water)



TGA data for FC-4430

This data shows the excellent thermal stability of Novec FC-4430 fluorosurfactant if used in a thermal processing application.

(10 mg sample heated at 5 °C / min. in air)

Temperatures (°C) at which specified % wt. loss occur

	5%	10%	50%	80%	90%	95%
FC-4430	195	255	305	330	355	405

Regulatory Summary

- Not considered persistent, bioaccumulative and toxic (PBT) under the U.S. Environmental Protection Agency's (EPA) PBT Chemical Policy
- The first series of PFBS-based surfactants produced by 3M have been reviewed by the U.S. EPA and placed on the TSCA inventory. There is a testing consent order in place. The products are exempt from reporting in Europe because they meet the polymer exemption criteria and, in addition, all monomers are on the European chemical inventory (EINECS). The products are available for purchase in Australia, China, Korea, New Zealand, The Philippines and on a limited basis in Canada and Japan.
- PFBS and PFBS-based surfactants are not included in the U.S. EPA's PFAS Final Significant New Use Rule (SNUR 67FR 72584).

For additional country specific information, please contact 3M's Chemical Regulatory department: jfschulz@mmm.com

3M™ Novec™ Fluorosurfactant FC-4430 Packaging and Availability

Novec FC-4430 fluorosurfactant is currently available in:

- 8 lb. pail
- 40 lb. pail
- 250 lb. drum

For additional literature, MSDS or to request a 2 oz sample, visit our website:
www.3m.com/paintsandcoatings.

3M™ Novec™ Fluorosurfactant FC-4430 Product Safety and Handling

3M™ Novec™ Fluorosurfactant FC-4430 is intended for use in non-dispersive applications.

3M does not recommend this product for use in applications involving repeated exposure thorough skin contact, inhalation, or ingestion. It is not intended for cosmetic or medical usage. Neither 3M nor the Food and Drug Administration has evaluated or reviewed this product for food or pharmaceutical applications.

It is the buyer's responsibility to determine whether this product is durable and properly cured for the end use. This will help minimize environmental impact by ensuring the coating is not easily removed nor disposed to a waste water treatment facility. Incinerate in an industrial or commercial facility in the presence of a combustible material. Combustion products will include HF. Facility must be capable of handling halogenated materials. As a disposal alternative, dispose of waste product in a facility permitted to accept chemical waste. For further information, see the product Material Safety Data sheet.

3M Resources

To place an order or to request additional information, please contact your local 3M representative, an authorized 3M distributor or call 1 800 541 6752.

United States

3M Performance
Materials Division
800 541 6752

Brazil

3M do Brasil Ltda.
5519 3838 7000

Canada

3M Canada Company
800 364 3577

Europe

3M Belgium N.V.
32 3 250 7521

India

3M India Limited
Bangalore
9080 2231414

China

3M China Ltd.
86 21 6275 3535

China

3M Hong Kong Limited
852 2806 6111

Taiwan

3M Taiwan Limited
886 2 2704 9011

Korea

3M Korea Limited
82 2 3771 4114

Japan

Sumitomo 3M Limited
813 3709 8250

Philippines

3M Philippines, Inc.
63 2 813 3781

Singapore

3M Singapore Pte. Ltd.
65 454 8611

Malaysia

3M Malaysia Sdn. Berhad
60 3 706 2888

New Zealand

3M New Zealand Ltd.
64-9-444-4760

Australia

3M Australia Pty., Ltd.
61 2 9498 9333

Other Areas

651 736 7123 (U.S.)

Important Notice to Purchaser: The information in this publication is based on tests that we believe are reliable. Your results may vary due to differences in test types and conditions. You must evaluate and determine whether the product is suitable for your intended application. Since conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties (including the implied warranties of merchantability or fitness for a particular purpose): Except where prohibited by law, 3M's only obligation and your only remedy, is replacement or, at 3M's option, refund of the original purchase price of product that is shown to have been defective when you received it. In no case will 3M be liable for any direct, indirect, special, incidental, or consequential damages (including, without limitation, lost profits, goodwill, and business opportunity) based on breach of warranty, condition or contract, negligence, strict tort, or any other legal or equitable theory.



3M Performance Materials Division

3M Center, Building 223-6S-04
St. Paul, MN 55144-1000

www.3m.com/paintsandcoatings

3M, Fluorad and Novec are trademarks of 3M Company.
Used under license by 3M subsidiaries and affiliates.

Issued: 10/03

© 2003 3M

4695(HB)
98-0212-3716-3