Part#: 37BC28

Part#	Description	Dimensions	Weight	Capacity
37BC28	Rapid Rise Model Containment Berm	15'x66'x1'	357 lbs	7,405 Gallons

Photo does not depict actual size.

Supplied By: **The Cary Company**
Ph: 630-629-6600
www.thecarycompany.com

SPECIFICATIONS

KEY FEATURES AND BENEFITS

- Sidewalls remain down during normal operations, loading and unloading. Vehicles and equipment can drive in and out with no set-up or take-down required
- In the case of a spill, the foam ring around the top perimeter of the Containment Berm rises with the level of spilled liquid.
- Standard material of construction is Copolymer 2000™.

SIDEWALLS:

- Lay flat unless spill occurs - foam ring will rise with liquid level.
- Eliminates tripping hazards.
- No set-up required once Berm has been positioned in the field.

COMPLIANCE:

- EPA 40 CFR 264.175 Containment of Containers Containing Free Liquid.
- SPCC - Spill Prevention, Control and Countermeasure Act

STANDARD SIZES AVAILABLE

	Size	Capacity	Weight
Part# 8430	4' x 6' x 1'(1.2 m x 1.8 m x .3 m)	179 gallons (678 L)	29 lbs. (13 kg)
Part# 8431	6' x 6' x 1'(1.8 m x 1.8 m x .3 m)	269 gallons (1,018 L)	35 lbs. (16 kg)
Part# 8432	10' x 10' x 1'(3 m x 3 m x .3 m)	748 gallons (2,831 L)	63 lbs. (29 kg)
Part# 8437	12' x 26' x 1' (3.7 m x 7.9 m x .3 m)	2,333 gallons (8,831 L)	149 lbs. (67.5 kg)
Part# 8433	15' x 50' x 1'(4.6 m x 15.2 m x .3 m)	5,610 gallons (21,234 L)	278 lbs. (126.5 kg)
Part# 8434	15' x 66' x 1'(4.6 m x 20.1 m x .3 m)	7,405 gallons (28,028 L)	357 lbs. (162 kg)
Custom Sizes Available.			

MATERIAL SPECIFICATIONS (Specs shown are for Copolymer-2000. Other materials available.)

Reinforced	Standard	Metric
Base Fabric Type	Polyester	
Base Fabric Weight (nominal)	3.0 oz/yd^2	102 g/m^2
Finished Coated Weight - ASTM D751	28.0 $\pm$ 2 oz/yd^2	950 $\pm$ 70 g/m^2
Thickness - ASTM D751	30 mils nominal	0.76 mm nominal
Trapezoid Tear - ASTM D4533	30/30 lb_f nominal	133/133 N nominal
Grab Tensile - ASTM D751 Grab Method	250/200 lb_f min.	1112/890 N min.
Hydrostatic Resistance - ASTM D751, Procedure A	300 psi min.	2.06 MPa min.
Adhesion - ASTM D751 Dielectric Seam	10 lb_f/in min.	9.0 daN/5 cm min.
Cold Crack - ASTM D2136 1/8 in mandrel, 4 hr.	Pass @ -25° F	Pass @ -32° C
Puncture Resistance - ASTM D4833	50 lb_f typical	225 N typical
Dead Load - ASTM D751	2 in seam, 4 hr, 1 in strip 100 lb_f @ 70° F 50 lb_f @ 160° F	5 cm seam, 4 hr, 2.5 cm strip 445 N @ 21° C 220 N @ 70° C

THE CARY COMPANY Est. 1895

PH 630-629-6600 - FX 630-629-3690
1195 W. FULLERTON AVE. - ADDISON, IL 60101
WWW.THECARYCOMPANY.COM