


IF YOU...



MIX IT. FILL IT. PACK IT. SHIP IT.

WE HAVE A **PRODUCT** FOR YOU

Part #: 68WCT3

Adhesive Foam Tape

3" x 25' Adhesive Foam Tape, EPDM/Neoprene/
SBR Closed Cell, 1" Thick



The
CARYCOMPANY
Est. 1895

1195 W. Fullerton Ave. | Addison, IL 60101 | T: 630.629.6600 | F: 630.629.3690 |

Neoprene / EPDM / SBR Closed Cell Foam Tape

TECHNICAL DATA

- Absorb shock and dampen sound and vibrations
- Provide a tight, long-lasting seal against moisture, dust, and air leaks
- Pass FMVSS302 and UL 94 HF1 for flammability
- Resist acids, alkali, ozone, and oxidation

Product Description Neoprene/EPDM/SBR blend tape featuring a high-tack rubber based pressure sensitive adhesive (PSA) on one side with easy-to-use release liner.

NOTE: Also available with acrylic PSA on one-side (minimums may apply)

P8100 (SC 42-UL) is a general application tape recommended for gasketing and weatherproofing windows and doors.

STANDARD ROLL SIZE	SERIAL NUMBER	THICKNESS	LENGTH	
P8100 (SC 42-UL) is available in widths from 1/4" to 54 inches wide.	P8106 (SC 42-UL)	1/16"	50'	
	P8112 (SC 42-UL)	1/8"	50'	
	P8118 (SC 42-UL)	3/16"	50'	
	P8125 (SC 42-UL)	1/4"	50'	
	P8137 (SC 42-UL)	3/8"	25'	
	P8150 (SC 42-UL)	1/2"	25'	
	P8175 (SC 42-UL)	3/4"	25'	
	P811	1"	25'	
ADHESION PROPERTIES	TEST	TYPICAL PERFORMANCE	TEST METHOD	
High-tack pressure sensitive rubber based adhesive. One sided with release liner.	Adhesion to Steel @ 72°F Steel immediate Steel after 24 hours	7 lbs/inch width or foam tear 8 lbs/inch width or foam tear	PSTC-1 PSTC-1	
	Adhesion to Steel, 20 minute dwell	10 lbs/in width minimum	PSTC-1	
	Static Shear @ 72°F 1 x 1 x 500 grams	1000 hours minimum	PSTC-7	
	Static Shear @ 72°F 1 x 1 x 1000 grams	200 hours minimum	PSTC-7	
	Shelf Life	1 year stored at room temperature		
PHYSICAL PROPERTIES	P8100 TAPE (MEDIUM DENSITY)	TEST METHOD	UNIT OF MEASURE	RESULT
	Density (PCF)	ASTM D1056	PCF kg/cm3	4-8 .064-.128
	ASTM-D-1056-67 Grade #	--	--	SCE 42
	ASTM-D-1056 07	--	--	2C2
	Service Temperature	--	F	-40F to +250F
	Water Absorption (Max)	ASTM D1056	%	5
	Tensile Strength (Min)	ASTM D412 (DIE A)	PSI kPa	75 517
	Elongation (Min)	ASTM D412 (DIE A)	%	150
	Compression Deflection 25%	ASTM D1056	psi	5 - 9
	Compression Set (Max)	ASTM D1056	%	25
	Flammability (UL 94 HF1, FMVSS302)	UL E208679	Pass/Fail	Pass
	UL 50, UL 50E, UL 157, UL 508	UL JMLU2, MH10200	Pass/Fail	Pass
	Durometer	ASTM D1056	Shore 00	30-50