



Freshness and Protection
for Today's Packaging

FoilSeal™ Data Sheet

.030" C25P FS 1-15

Revision: FS115-01152007

Product	.030" C25P FS 1-15																							
Scope	Two piece foam backed heat induction foil innerseal that provides an aggressive bond with clean peel removal from PE and PP containers with added barrier layer for sealing aggressive products.																							
Composition	<table border="1"> <thead> <tr> <th>Material</th> <th>Standard</th> <th>Metric</th> </tr> </thead> <tbody> <tr> <td>Backing</td> <td>.030"</td> <td>.762 mm</td> </tr> <tr> <td>Paper</td> <td>.005"</td> <td>.127 mm</td> </tr> <tr> <td>Wax</td> <td>-</td> <td>-</td> </tr> <tr> <td>Foil</td> <td>.001"</td> <td>.0254mm</td> </tr> <tr> <td>PET</td> <td>.0005"</td> <td>.0127mm</td> </tr> <tr> <td>Heat Seal</td> <td>.002"</td> <td>.0508mm</td> </tr> </tbody> </table>	Material	Standard	Metric	Backing	.030"	.762 mm	Paper	.005"	.127 mm	Wax	-	-	Foil	.001"	.0254mm	PET	.0005"	.0127mm	Heat Seal	.002"	.0508mm		
Material	Standard	Metric																						
Backing	.030"	.762 mm																						
Paper	.005"	.127 mm																						
Wax	-	-																						
Foil	.001"	.0254mm																						
PET	.0005"	.0127mm																						
Heat Seal	.002"	.0508mm																						
Composition does not include adhesive, resin or wax bonding layers (if any).																								
FDA Status:	21 CFR 177.1210	Recommended Storage and Handling:																						
Drug Master File (DFM):	#4544	Canadian DMF:	EU / EP Reg.:																					
GTR Oxygen:	Essentially Zero	MVTR:	Essentially Zero																					
Print Location (if any):	Foil Layer and/or Heat Seal Layer																							

Selig materials are compliant with current USFDA Food allergen Guidelines.
Selig materials are compliant with California Proposition 65 labeling requirements.
Selig materials are compliant with limitation of heavy metals in packaging per CONEG & EU 94/62/EC, article 11.

MSDS's are not required as Selig is not a chemical manufacturer or distributor and our products are 'articles' intended for food packaging per 29 CFR 1910.1200 (HazCom).

The information contained within this product data bulletin is to be used as a general guide in determining which structures are offered for sealing to specific container materials. All of the information which we provide is reliable to the best of our knowledge, but the accuracy thereof is not guaranteed. We suggest that consumers determine suitability for their own application.

www.seligsealing.com

Corporate Headquarters
Selig Sealing Products, Inc.
342 E Wabash St
Forrest, IL 61741, USA
Phone: +1 (815) 785-2100
Fax: +1 (815) 657-7584

North American Sales
Selig Sealing Products, Inc.
184 Shuman Blvd., Suite 310
Naperville, IL 60563, USA
Phone: +1 (630) 922-3158
Fax: +1 (630) 922-8469

European Sales and Manufacturing
Selig UK, LTD 635-637 Ajax Avenue
Slough Trading Estate
Slough Berkshire SL14BH UK
Phone: +44 (0) 1753 773 000
Fax: +44 (0) 1753 773 111

Canadian Manufacturing
Selig Canada, ULC
145 Edward Street
Aurora, Ontario Canada, L4G 1W3
Phone: +1 (905) 727-0114
Fax: +1 (905) 727-8544

Swiss Manufacturing
Selig Switzerland LTD
Bahnhofstrasse 11
CH-8172 Niederglatt
Phone: +41 (0) 44 851 50 50
Fax: +41 (0) 44 851 50 51

