

FoilSeal™ Technical Data Sheet

.035" C25P FS 3-19

Revision: FS319-07282014

Product	.035" C25P FS 3-19																				
Scope	Two piece foam backed heat induction foil innerseal that will provide an aggressive bond with clean peel removal from PET and PVC containers. (Not recommended for use on CPET. Easy access / "puncture foil" when wax bonded to pulp.																				
Composition	<table border="1"> <thead> <tr> <th>Material</th> <th>Standard</th> <th>Metric</th> </tr> </thead> <tbody> <tr> <td>Backing</td> <td>.035"</td> <td>.889 mm</td> </tr> <tr> <td>Paper</td> <td>.005"</td> <td>.127 mm</td> </tr> <tr> <td>Wax</td> <td>-</td> <td>-</td> </tr> <tr> <td>Foil</td> <td>.001"</td> <td>.0254mm</td> </tr> <tr> <td>Heat Seal</td> <td>.0005"</td> <td>.0127mm</td> </tr> </tbody> </table>	Material	Standard	Metric	Backing	.035"	.889 mm	Paper	.005"	.127 mm	Wax	-	-	Foil	.001"	.0254mm	Heat Seal	.0005"	.0127mm		
Material	Standard	Metric																			
Backing	.035"	.889 mm																			
Paper	.005"	.127 mm																			
Wax	-	-																			
Foil	.001"	.0254mm																			
Heat Seal	.0005"	.0127mm																			
Adhesive or resin bonding layers not shown.																					
FDA Status: 21 CFR 177.1210	Recommended Storage and Handling: Refer to Website																				
Drug Master File (DMF): #4544	EU / EP Reg.:																				
GTR Oxygen: Essentially Zero	MVTR: Essentially Zero																				
Print Location (if any): Foil Layer and/or Heat Seal Layer																					

The
CARY COMPANY
Est. 1895

